

Dunwood Polymer Services Ltd  
 Genesys House  
 Sandbeck Way  
 Wetherby  
 LS22 7DN  
 Tel : +44 1937 548318  
 Fax : +44 1937 589111  
 www.dunwood.com



## EMUPOL 6650-34

### GENERAL INFORMATION

Colloid stabilised, vinyl acetate/VeoVa/Acrylic ester copolymer dispersion containing no external plasticisers.

### PROPERTIES AND USES

Emupol 6650-34 gives good adhesion to polystyrene insulating beads.

Additional technical information is available from our technical staff.

Typical Data			
Total Solids	%	33.0 – 35.0	ISO 3251
pH	-	4.0 – 5.0	ISO 976
Viscosity	mPa s	0 – 200	ISO 2555
Typical Properties			
Particle Size	μ	0.3	
Minimum Film Forming Temperature	°C	0	
Glass Transition Temperature	Onset	°C	
	Midpoint	-26	
Specific Gravity		-36	
		1.07	

### HEALTH AND SAFETY

Please refer to the Material Safety Data Sheet for safety and environmental information. Emupol 6650-34 is not classified as dangerous according to EU Directive 1999/45/EC and does not require any special labelling.

### STORAGE AND HANDLING

Store at an even temperature of between +5°C and +35°C avoiding frost and direct sunlight. Stir product before use. If stored according to these conditions and in the original unopened containers, the dispersion will be stable for 6 months following delivery. Product should be used as soon as possible after opening. Detailed information is available on request.